

ABSTRACT

09913332-081301

Provided is a thermoplastic resin composition comprising (A) a styrene resin, (B) a propylene resin and (C) a hydrogenated block copolymer comprising at least two polystyrene blocks Xs and at least one polybutadiene block Y, with at least 70 wt.% of the double bonds of the polybutadiene of the polybutadiene block Y having been hydrogenated, wherein the hydrogenated block copolymer (C) has a styrene content of 40 to 80 wt.%; a 1,2-bound amount of the polybutadiene block Y is 30 to 80 wt.%; a weight ratio of the component (A) to the component (B) is 95:5 to 5:95; the component (C) is contained in an amount of 2 to 30 parts by weight based on 100 parts by weight of the components (A) and (B); and at least 50% of the component (C) exists at the interface between a phase of the component (A) and a phase of the component (B). Existence of this component (C) makes it possible to yield a thermoplastic resin composition having excellent heat resistance and oil resistance and having comparable tensile elongation properties.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08L 25/00, 51/04		A1	(11) International Publication Number: WO 93/13168 (43) International Publication Date: 8 July 1993 (08.07.93)
(21) International Application Number: PCT/US92/09091 (22) International Filing Date: 27 October 1992 (27.10.92) (30) Priority data: 07/811,350 20 December 1991 (20.12.91) US 07/859,207 27 March 1992 (27.03.92) US (60) Parent Application or Grant (63) Related by Continuation US 07/859,207 (CIP) Filed on 27 March 1992 (27.03.92) (71) Applicant (for all designated States except US): THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Abbott Road, Midland, MI 48640 (US).		(72) Inventors; and (75) Inventors/Applicants (for US only) : SWARTZMILLER, Steven, B. [US/US]; 2901 Valorie Lane, Midland, MI 48640 (US). DONALD, Robert, J. [US/US]; 5503 Win- chester Court, Midland, MI 48640 (US). BONEKAMP, Jeffrey, E. [US/US]; 2901 Braley Court, Midland, MI 48640 (US). (74) Agent: DELINE, Douglas, N.; The Dow Chemical Com- pany, Patent Department, P.O. Box 1967, Midland, MI 48641-1967 (US). (81) Designated States: AU, CA, JP, KR, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, SE). Published With international search report.	
(54) Title: THERMOFORMABLE, CHEMICAL RESISTANT POLYMER BLENDS			
(57) Abstract A thermoformable chemical resistant polymer blend, useful in the preparation of refrigerator and freezer liners compris- ing: A) from 45 to 70 parts by weight impact modified monovinylidene aromatic polymer, comprising from 1 to 25 weight percent of a rubber and 75 to 99 weight percent of a monovinylidene aromatic polymer matrix having a molecular weight (Mw) from 50,000 to 400,000, said weight percents being based on the total weight of said impact modified, vinylaromatic polymer; B) from 15 to 40 parts by weight of an olefin polymer, selected from the group consisting of homopolymers of ethylene or propylene and copolymers of ethylene with one or more C ₄₋₈ α-olefins; and C) from 5 to 25 parts by weight of a compatibilizing polymer, adapt- ed to increase interfacial adhesion between components A) and B), components A) and B) or components A), B) and C) existing in said blend as co-continuous phases, and the sum of A), B) and C) being 100 parts.			

09913332, 081301